




BST DetectaWipe® Drywipe Marker | DW-*



Product Description

The body & cap of our Detecta-Wipe Markers are moulded from high-density polyethylene, containing a non-toxic metal detectable additive.

This compound can be detected by correctly calibrated in-line metal and x-ray detection systems.

The Detecta-Wipe features Sureflow ink, meaning the pen will continue to write for several days, even if the cap is left off. This ink is suitable for use on whiteboards and other glossy surfaces that can be wiped clean with a cloth or tissue.

DetectaWipe® Drywipe Marker Advantages

- ✓ Detectable by in-line metal detection systems & x-ray inspection systems
- ✓ Highly visible bright blue body colour for easy visual identification
- ✓ Wipes clean from whiteboards and other glossy surfaces
- ✓ Available with standard and fine tip nibs in a variety of ink colours to suit specific requirements
- ✓ Sureflow ink means the pen will continue to write for several days with the cap left off
- ✓ Compliant with EU & FDA food contact legislation, including mandatory EU migration test standards
- ✓ Can be used as part of HACCP and BRC procedures
- ✓ Displays due diligence in the prevention of foreign body contamination

Product and Packaging Information

Standard Nib Code	DW-*	Fine Tip Nib Code	WDF-*
Size (Standard Nib)	134mm x 18mmØ	Size (Fine Tip Nib)	120mm x 18mmØ
Standard Nib Ink	B,K,R,G	Fine Tip Ink	B,K
Write Out Length	700m +/- 20%	Write Out Length	400m +/- 20%
Body Colours	W 230 x H 355 x D 5.5mm	Coloured End Plug	LLDPE
Pack Size	10	Nib Material	Polyester
Pack Weight	0.20kg	Detectability	Metal & X-Ray Visible
Body Material	HDPE	Country Of Origin	Britain
Cap Material	HDPE	Commodity Code	39269097

Ink Specification

- ✓ EN 71-3:2013 + A1:2014
- ✓ EN71-9:2005+A1:2007
- ✓ EU / US / CA TRA
- ✓ ASTM D-4236 TRA

Safety Certificates / Approvals

FDA Approved	Kosher Certified	Made In Britain
EU Compliant	BRCGS Compliant	ISO 9001:2015



Handling and Storage

Store at normal room temperature, keep away from direct heat and keep in original container.

Ink Properties

This ink does not contain any substances of very high concern (SVHC), Benzene, Toluene or Xylene. This substance is not identified as a PBT substance.

Property	Value
Hazard Identification	With normal use, no known hazards.
Stability / Reactivity	Product is stable.
Eco Toxicity	No adverse ecological effects known.
Chemical Properties	The solvent based ink contains industrial meths, and will produce a flammable vapour that is heavier than air.
Volatility	80%
Specific Gravity	0.815 - 0.835

Ink Safety

Ink contact with skin is not considered hazardous when coming into contact with skin through normal use. In the event of abnormal use causing health problems please refer to the below information.

Route	First Aid
Oral	Give plenty of water to drink if ingestion is suspected.
Skin Contact	Wash skin with soap and water.
Eye Contact	Irrigate with water for ten minutes - obtain medical attention.
Inhalation	Remove from exposure - in severe cases obtain medical attention.

Ink Temperature Range

The drywipe ink will work in temperature ranges up to 50°C. They will also work in freezing temperatures however, if the cap is left off the nib for longer periods of time at freezing temperatures the nib will solidify due to the surfactant additive that is used to stop the ink from drying out.

Animal Derivatives

To the best of our knowledge there are no ingredients in the formulation of this material that is of animal origin. As such, this material should not pass on any animal derived disease like BSE (Bovine Spongiform Encephalopathy) or other TSE (Transmissible Spongiform Encephalopathy).

Migration Testing

The following overall migration results for HDPE were obtained using a UKAS accredited laboratory, with overall migration simulants and conditions as detailed in EU Regulation No 10/2011 as amended, with regards to use with all food types (no fatty food factor applied).

Sample: HDPE-2016/138

Test conditions: 10 days at 40°C

Method	EN-1186-3 Migration into 10% v/v Ethanol (Simulant A)	EN-1186-3 Migration into 3% w/v Acetic Acid (Simulant B)	EN-1186-2 Migration into Olive Oil (Simulant D2)
Replicate #1	0.4 mg/dm ²	0.6 mg/dm ²	1.3 mg/dm ²
Replicate #2	0.2 mg/dm ²	0.4 mg/dm ²	0.0 mg/dm ²
Replicate #3	0.1 mg/dm ²	0.5 mg/dm ²	0.0 mg/dm ²
Replicate #4			1.9 mg/dm ²
Mean Result	0.2 mg/dm ²	0.5 mg/dm ²	0.8 mg/dm ²
EU Limit	10.0 mg/dm ²	10.0 mg/dm ²	#10.0 mg/dm ²

#Limit and tolerance are quoted after the application of a fatty food reduction factor of 2 as quoted in EU Regulation 10/2011

To summarise the overall migration test results, the HDPE complies with the overall migration requirements given in EU Regulation 10/2011, as amended, with regards to use with all non-fatty foods, aqueous foods and fatty foods that require a reduction factor of 2 (or greater), as given in EU regulation 10/2011, as amended.

Food Contact Status (EU) HDPE Material (Body & Cap)

Hereby we declare that the material HDPE is manufactured in line with the relevant requirements of 2023/2006/EC as amended by Commission Regulation (EC) 282/2008, on good manufacturing practice (GMP) for materials and articles intended to come into contact with food.

The raw materials used in the manufacturing process of the above mentioned materials can be considered suitable for food contact applications in terms of compliance with European regulations. The raw materials used meet the relevant requirements of EU Framework Regulation 1935/2004 on materials and articles intended to come into contact with food.

All monomers, starting substances and additives used to manufacture these grades are listed in Commission Regulation (EU) No.10/2011 as amended by (EU) 321/2011, (EU) 1282/2011, (EU) 1183/2012, (EU) 202/2014, (EU) 2015/174, (EU) 2016/1416, (EU) 2017/752, (EU) 2018/79, (EU) 2018/213, (EU) 2018/831, (EU) 2019/37, (EU) 2019/1338, and (EU) 2020/1245 respectively, related to Plastic Materials and Articles intended to come into contact with foodstuffs. Colourants used are compliant with European Council Resolution AP(89) 1 on the use of colourants in plastic materials coming into contact with food, and also with German BfR Recommendations (IX).

Food Contact Status (FDA) HDPE Material (Body & Cap)

The polypropylene base resin used in HDPE meets the FDA (Food and Drug Administration) requirements contained in the Code of Federal Regulations in 21 CFR 177.1520. At the same time this base resin grade meets the FDA criteria in 21 CFR 177.1520 for food contact applications, excluding cooking, listed under conditions of use C through H in 21 CFR 176.170 (c), Table 2., and can be used in contact with all food types as listed in 21 CFR 176.170 (c), Table 1. Also the mineral additives and the pigments used are GRAS (Generally Recognized As Safe) or are FDA cleared under specific FDA citations.

Food Contact Status LLDPE Material (Coloured End Plug)

The raw materials used in the manufacturing process of LLDPE are compliant with the Commission Regulation (EU) No. 10/2011 on plastic materials intended to come in to contact with food including its amendments. Under FDA regulations, the listed material is confirmed as generally recognized as safe (GRAS).

DetectaMark® Metal Detectability

The body, cap and plug of our markers are manufactured from detectable polymers. These polymers contain evenly dispersed non-toxic detectable additives, making the material detectable by correctly calibrated metal detection systems and x-ray inspection systems. Metal detectability performance will vary based on, but not limited to the following factors:

- Calibration Levels
- Product Type (E.g. Wet, Dry, Frozen, Liquid)
- Aperture Dimensions
- Orientation

Orientation is a highly influential factor for the metal detectability of a contaminant that is non spherical, i.e. it will be easier to detect the contaminant when passing in one orientation compared to another - this is known as the orientation effect.

For this reason BST recommend that all our products be thoroughly tested on your metal detection systems by a trained and certified professional. It may be the case that your equipment needs to be re-calibrated in order to reliably detect this product. Such a professional should be available by contacting the manufacturer of your metal detection system.

DetectaMark® X-Ray Visibility

In contrast to metal detection, x-ray visibility is determined by material density. For this reason, our markers contain an additional, evenly dispersed, food safe, high density additive. X-ray detection performance will be reduced when small fragments are buried in deeper, denser products - detection will depend on product type and density.

We highly recommend that all our products be thoroughly tested on your x-ray inspection systems by a trained and certified professional. It may be the case that your equipment needs to be recalibrated in order to reliably detect this product. Such a professional should be available by contacting the manufacturer of your x-ray inspection system.

The information provided in this product specification sheet is based on our experience and knowledge to date and we believe it to be true and reliable. This information is intended as a guide for your use of our products, the use of which is entirely at your own discretion and risk. We, BS Teasdale & Son Ltd, cannot guarantee favourable results and assume no liability in connection with the use of our products. © 2023 BS Teasdale & Son Ltd. All Content, Data & Images are owned by BS Teasdale & Son Ltd and are protected by international copyright law.